

### Storage properties of Frenzelit Gasket Materials (Sheets)

#### Storage recommendations according to ISO 2230

- Room temperature in the warehouse < 25°C
- Air humidity < 65% rel. humidity
- Do not expose to direct sunlight
- Principle of storing „FIFO“ „First In – First Out“

#### Recommendation for novaphit<sup>®</sup>-, novafilon<sup>®</sup>- und novamica<sup>®</sup> range

Storing time: unlimited

#### Recommendation for novapress<sup>®</sup>-, novatec<sup>®</sup> und novaform<sup>®</sup> range

Due to marginal percentage of elastomers in the fibre-reinforced gasket materials we recommend to observe the above recommendations strictly.

These recommendations are determined and proved by long-term tests with respect to important sealing properties.

Storage time of novapress<sup>®</sup>- und novatec<sup>®</sup>-range und novaform<sup>®</sup>: not less than 5 years

**Remark:** Especially in case of increase of ideal temperature of 25°C by 10°C over a longer period a reduced storage time by 50 pct is to be expected.

Application engineering questions?

We help you at: [gaskets@frenzelit.com](mailto:gaskets@frenzelit.com), Phone: +49 9273 72-140

Status: May 2018