

Storage properties of Frenzelit Gasket Materials (Sheets)

Storage recommendations according to ISO 2230

- Room temperature in the warehouse < 25°C
- Air humidity < 65% rel. humidity
- Do not expose to direct sunlight
- Principle of storing „FIFO“ „First In – First Out“

Recommendation for novaphit[®]-, novafon[®]- und novamica[®] range

Shelf life: unlimited

Recommendation for novapress[®]-, novatec[®] und novaform[®] range

Due to marginal percentage of elastomers in the fibre-reinforced gasket material, it is recommended to observe the above recommendations strictly.

These recommendations are determined and proved by long-term tests with respect to important sealing properties.

Shelf life of novapress[®]- und novatec[®]-range und novaform[®]: at least 5 years

Remark: Especially in case of increase of the storage temperature of 25°C by 10°C over a longer period of time a reduction of storage time by 50 % is expected.

Application engineering questions?

We help you at: gaskets@frenzelit.com, Phone: +49 9273 72-140

Status: October 2021