

TechInfo 2

Storage properties of Frenzelit Gasket Materials (Sheet Material)

Storage recommendations according to ISO 2230

- Room temperature in the warehouse < 25°C
- Air humidity < 65% rel. humidity
- Do not expose to direct sunlight
- Principle of storing „FIFO“ „First In – First Out“

Recommendation for novaphit®-, novaflo®- und novamica® range

Storing time: unlimited

Recommendation for novapress®-, novatec® und novaform® range

Due to marginal percentage of elastomers in the fibre-reinforced gasket materials we recommend to observe the above recommendations strictly.

These recommendations are determined and proved by long-term tests with respect to important sealing properties.

Storage time of novapress®- und novatec®-range und novaform®: 5 years

Remark: Especially in case of increase of ideal temperature of 25°C by 10°C over a longer period a reduced storage time by 50 pct is to be expected.

Do you have any questions about your application? Our gaskets application engineering will help you:

gaskets@frenzelit.de, Phone: +49 9273 72-140

Status: May 2018