

**Gasket Constants acc. ASTM F3149-15 / ASME Code**

Gasket material	thickness [mm]	m	y [psi]	y [N/mm <sup>2</sup> ]
<b>novaflo<sup>®</sup> 100</b>	1.0	2.3	1160	8
	2.0	2.3	1160	8
	3.0	2.3	1160	8
<b>novaflo<sup>®</sup> 200</b>	1.0	2.8	2175	15
	2.0	2.8	2175	15
	3.0	2.8	2175	15
<b>novaflo<sup>®</sup> 300</b>	1.0	2.8	2175	15
	2.0	2.8	2175	15
	3.0	2.8	2175	15
<b>novaflo<sup>®</sup> 500</b>	1.0	2.8	2755	19
	2.0	2.8	2755	19
	3.0	2.8	2755	19

All previous data cease to apply. You may take all current versions from the website [www.frenzelit.com](http://www.frenzelit.com) or ask at Frenzelit directly. The values have been determined with standard laboratory equipment. In view of the variety of different installation and operation conditions and process engineering options, there is no basis for warranty claims referring to the behaviour of the sealing joint. Subject to technical changes and printing errors.

ver. 19-03