

novaform® SK

The industrial exhaust gasket for extremely tough mechanical conditions.



Material profile

High-quality aramid fibres and functional fillers are the basic materials used to manufacture novaform® SK, reinforced by a galvanised zigzag twill fabric (1.0314), homogeneously embedded in an NBR matrix.

This raw material blend gives novaform® SK following excellent material properties:

- extremely high tensile strength
- outstanding pressure resistance
- maximum temperature stability
- unique mechanical resistance and reliability
- stable long-term sealing properties, even under extreme conditions

Application areas

novaform® SK is the ideal choice for use in the exhaust section of diesel engines, for example in shipbuilding:

- for extreme thermal and mechanical conditions, particularly for hot exhaust gases, e.g. for exhaust systems, exhaust turbochargers, compressors
- can be combined very effectively with inner eyelet

Good for people and the environment

The Frenzelit gasket division has obtained certification that the company complies with the requirements of ISO 9001, ISO 14001 and ISO 50001.

This means complete transparency in all areas and therefore provides a high degree of security for the benefit of our employees, the environment and our customers.

If you have any application engineering questions, we will be delighted to answer them. Just contact:

application@frenzelit.com

GASKETS

TECHNICAL TEXTILES

EXPANSION JOINTS

INSULATION


NEW MATERIALS


creating hightech solutions

Technical information about novaform® SK

Recommendation for hot exhaust fumes

Depending on pressure and temperature levels




The temperature and pressure recommendations in the graphs apply to gaskets with a thickness of 2.0 mm and raised face flanges. Higher stresses are possible when thinner gaskets are used! The information provided must therefore be considered as estimates that are on the safe side rather than as specific operational limits.

Exact data for specific individual cases are available in the Frenzelit **novaDISC** programme or contact our application engineering specialists.



Temp-Test

at 50 MPa - sample thickness 2.0 mm



Explanatory notes about the temperature test (Temp-Test):

The purpose of the temperature test is to determine how the gasket deforms under certain conditions. It is a special Frenzelit development that represents what is effectively a "fingerprint" of major gasket properties.

The compression set of the gasket at room temperature is determined in the first part of the test. This curve indicates the adaptability of the gasket during installation.

In the second part of the test, the temperature is increased at a specified speed, while the surface pressure level reached in the first part is maintained consistently. I.e. the system is not allowed to "relax" as a result of gasket compression. This is overly critical – the strain on the gasket would be lower in a real sealing situation – but it unsparingly reveals the character of the gasket.

Material data

General data

Approvals and tests	GL
Colour	dark grey
Treatment	rolled-on graphite layer

Physical properties

Gasket thickness 2.0 mm

Standard	Unity	Value*	
DIN 28 090-2	[g/cm ³]	1.90	
DIN 52 913	[N/mm ²]	40	
ASTM F 36 J	[%]	15	
ASTM F 36 J	[%]	33	
DIN 52 910	[N/mm ²]	22	
ASTM F 146			
ASTM IRM 903	5 h/ 150 °C		
	Weight change	[%]	25
	Thickness increase	[%]	2
ASTM Fuel B	5 h/ 23 °C		
	Weight change	[%]	20
	Thickness increase	[%]	2
Coolant/Water (50:50)	5 h/ 100 °C		
	Weight change	[%]	30
	Thickness increase	[%]	3

*Mode (typical value)

Product data (tolerances acc. to DIN 28 091-1)

Dimensions	Roll: width 1000 mm, length approx. 10 m (+/- 30 % possible) Sheet: 1000 x 1000 mm (as roll section)
Thicknesses [mm]	1.0 / 1.2 / 1.5 / 2.0 / 3.0

Warranty disclaimer

In view of the variety of different installation and operation conditions and applications and processing engineering options, the information given in this prospectus can only provide approximate guidance and cannot be used as the basis for warranty claims.

GASKETS

TECHNICAL TEXTILES

EXPANSION JOINTS

INSULATION

NEW MATERIALS

Frenzelit GmbH
P.O. Box 11 40
95456 Bad Berneck
Germany
Phone +49 9273 72-0
Fax +49 9273 72-221
info@frenzelit.com
www.frenzelit.com

 **Frenzelit**
creating hightech solutions