

Gasket Constants acc. ASTM F3149-15 / ASME Code

Gasket material	thickness [mm]	m	y [psi]	y [N/mm ²]
novamica[®] THERMEX	1.0	2.3	4060	28
	2.0	2.3	4350	30
	3.0	2.3	4785	33
novamica[®] 200	1.0	2.8	4060	28
	2.0	2.8	4350	30
	3.0	2.8	4785	33

All previous data cease to apply. You may take all current versions from the website www.frenzelit.com or ask at Frenzelit directly. The values have been determined with standard laboratory equipment. In view of the variety of different installation and operation conditions and process engineering options, there is no basis for warranty claims referring to the behaviour of the sealing joint. Subject to technical changes and printing errors.

ver. 19-03