



Company Address	Frenzelt GmbH; Frankenhammer; 95460 Bad Berneck	According to <b>DIN EN 13555</b> <b>2014-07</b>
Gasket Type	novaphit® 400 mit XP-Technologie	
Sealing element dimensions [mm]	92x49x0.5	

L [mg/(s*m)]	Q <sub>min/L</sub> [MPa]	Q <sub>Smin/L</sub> [MPa]										
		Q <sub>A</sub> = 10 MPa	Q <sub>A</sub> = 20 MPa	Q <sub>A</sub> = 40 MPa	Q <sub>A</sub> = 60 MPa	Q <sub>A</sub> = 80 MPa						
10 <sup>0</sup>	5	5	5	5	5	5						
10 <sup>-1</sup>	5	5	5	5	5	5						
10 <sup>-2</sup>	5	5	5	5	5	5						
10 <sup>-3</sup>	25			8	5	5						
10 <sup>-4</sup>	76					64						
10 <sup>-5</sup>												
10 <sup>-6</sup>												
10 <sup>-7</sup>												
10 <sup>-8</sup>												



L [mg/(s*m)]	Q <sub>min/L</sub> [MPa]	Q <sub>Smin/L</sub> [MPa]										
		Q <sub>A</sub> = 10 MPa	Q <sub>A</sub> = 20 MPa	Q <sub>A</sub> = 40 MPa	Q <sub>A</sub> = 60 MPa	Q <sub>A</sub> = 80 MPa						
10 <sup>0</sup>	5	5	5	5	5	5						
10 <sup>-1</sup>	5	5	5	5	5	5						
10 <sup>-2</sup>	21			5	5	5						
10 <sup>-3</sup>	58				54	44						
10 <sup>-4</sup>												
10 <sup>-5</sup>												
10 <sup>-6</sup>												
10 <sup>-7</sup>												
10 <sup>-8</sup>												



Note: the content of darkened cells was not determined respectively is unnecessary      Rev - No: 1      Creation date of this sheet: 2018-10-24

