

Certificate

Gasket material: novapress® MULTI II
Type: DN40/ PN40
Test criteria: Compliance with the tightness criteria according to
TA-Luft [10⁻⁴ mbar · l/(m · s)]
standard: VDI-Guideline 2440 (edition November 2000)
VDI-Guideline 2200 (edition Juni 2007)
Test conditions:
initial gasket stress: 30 MPa
temperature of exposure : 200 °C
period of exposure : 48 h
test pressure (absolute) : 1 bar
period of leakage measurement: 24 h

measured leak rate: $4.7 \cdot 10^{-7}$ mbar · l/(m · s)
(Helium-leak detector)

Therefore the gasket is in compliance with the tightness criteria of 10⁻⁴ mbar · l/(m · s) and the gasket material can be regarded as **high-grade** sealing system for the purposes of **TA-Luft**.

This certificate is only valid in combination with our laboratory test report (Report Nr.: EMP-NR 17-07-045-PA-07-047) of 02.07.2007.

Bad Berneck, 23.01.2014

Frenzelit Werke GmbH



ppa. Bertram Axmann
General Manager Gasket Division



i.A. Andreas Will
Head of development/material testing

